



We help you shine.™



## ECLIPSE™ HARD FLOOR FLOOR SEALER

# 403 ECLIPSE™ HARD FLOOR

## FLOOR SEALER

A water-based acrylic formula sealer for concrete, stone and similar hard floor surfaces.

Our **quick drying** and **excellent** adhesive sealer.

### Product Packaging\*



**PROD CODE: 403FS**  
 SIZE: 2.5 US gallons (9.5 liters)  
 ORDER QTY: 2 per case



**PROD CODE: 403FSE**  
 SIZE: 2.64 US gallons (10 liters)  
 ORDER QTY: 2 per case

\*Multi-Language Label.



**PROD CODE: 403MPE**  
 SIZE: 1.06 US gallons (4 liters)  
 ORDER QTY: 4 per case

\*Multi-Language Label.

### Recommended Surfaces:

Concrete and most types of terrazzo, marble and quarry tile.

### Directions for use:

1. Strip floor with recommended floor stripper, stripping machine and pad or brushes manufactured by Amano Pioneer Eclipse.
2. Neutralize floor using a neutral cleaner or EnviroStar Green™ Neutralizer.
3. Rinse floor thoroughly with water twice and allow to dry.
4. Apply 2 thin coats of ECLIPSE Hard Floor Sealer with a clean synthetic mop. Allow floor to dry between coats.
5. Apply recommended floor coating manufactured by Amano Pioneer Eclipse. Follow label instructions. Burnish as desired.

NOTE: To prevent contamination do not pour unused product from bucket into original container.

\* Special packaging for specific requirements available upon request.

### Product Data:

<b>Description</b>	Polymer emulsion	<b>Coverage</b>	1500 ft <sup>2</sup> /gal first coat 37 m <sup>2</sup> /l 2500 to 3000 ft <sup>2</sup> /gal 61 to 74 m <sup>2</sup> /liter	<b>Detergent Resistance</b> ASTM D3207-92 (2008)	Excellent
<b>Appearance</b>	Milky white	<b>Fragrance</b>	Slight solvent	<b>Removability</b> ASTM D1792-06	Semi-permanent
<b>Non-volatile solids</b> ASTM D2834-95 (2008)	19%	<b>Slip Resistance</b> UL TM410	Meets requirements	<b>Drying Time</b>	About 30 minutes
<b>pH</b> ASTM E70-07	7.8	<b>Shelf Life</b> ASTM D1791-93 (2008)	1 year	<b>Freeze/Thaw</b> ASTM D3209-93 (2008)	Passes 3 cycles
<b>Viscosity (Brookfield)</b> @ 68°F (20°C)	<10 centipoise	<b>Density</b> ASTM D1475-98 (2008)	8.5 lb/gal @ 68°F 1.02 kg/L @ 20°C	<b>VOC</b> (40 CFR Part 59 Subpart C)	7.02 %

MSDS sheets available for download at [www.pioneer-eclipse.com](http://www.pioneer-eclipse.com)

