



We help you shine.™



POWERSTAR®
STAIN RESISTANT TOP SHIELD™

421 PowerStar®

shine on.

STAIN RESISTANT TOP SHIELD™

High performance micro-film forming surface treatment that hardens and protects concrete. Creates a breathable, ultra-hard, water repellent and dust-repelling surface.

Product Packaging*



PROD CODE: 421GL5
SIZE: 2.50 US gallons (9.5 liters)
ORDER QTY: 2 per case



PROD CODE: 421DR5
SIZE: 55 US gallons (208 liters)
ORDER QTY: unit

* Special packaging for specific requirements available upon request.

The **strongest** protection for **hard surface** floors.

Recommended Floor Surfaces:

Concrete, terrazzo, marble and quarry tile floors.

Directions for use:

1. Sweep floor to remove all loose debris and soils such as polishing dust, curing compounds, drywall residue, etc.
2. Clean floor with a pH neutral cleaner using an automatic scrubber equipped with a black strip pad to remove sealers, oils, greases, etc.
3. Allow surface to dry thoroughly.
4. Apply PowerStar Stain Resistant Top Shield thinly and evenly on the floor using a pump-up sprayer at an approximate coverage rate of 2000 ft² per gallon (49 m²/L) .
NOTE: DO NOT dilute PowerStar Stain Resistant Top Shield.
5. Spread the PowerStar Stain Resistant Top Shield evenly on the floor using a clean micro-fiber applicator or lint free flat fiber mop pre-sprayed with PowerStar Stain Resistant Top Shield.
6. Allow floor to dry thoroughly before applying a second coat.
Note: Approximate drying time is 30-60 minutes depending on temperature, humidity, floor conditions and amount of PowerStar Stain Resistant Top Shield applied.
7. Do not allow pedestrian or wheeled traffic on the floor for at least 2 hours. Do not allow water on the floor for at least 24 hours.
8. Burnish floor for enhanced gloss if desired.
9. Sweep floor regularly to remove loose debris and soils.
10. Scrub floor routinely with an automatic scrubber and a neutral cleaner.

Product Data:

Flash Point ASTM D56-05 (2010)	>200°F (93°C)	pH ASTM E70-07	11.0	Density ASTM D1475-98 (2008)	9.2 lb/gal @ 68°F 1.11 kg/L @ 20°C
Appearance	Milky white	Fragrance	None added	Shelf Life ASTM D1791-93 (2008)	1 year
Viscosity (Brookfield) @ 68°F (20°C)	<10 centipoise				

MSDS sheets available for download at www.pioneer-eclipse.com

Pioneer Eclipse®

©2011 Amano Pioneer Eclipse Corporation® • 1 Eclipse Road • PO Box 909 • Sparta, NC 28675 USA
1-800-367-3550 • 1-336-372-8080 • Fax: 1-336-372-2895 • www.pioneer-eclipse.com