



We help you shine.™

WOODSTAR™
WOOD FLOOR COATING

702 WOODSTAR™

WOOD FLOOR COATING

shine on.

Our *low odor* and *stable* wood floor coating.

An internally cross-linked, one component, water based, commercial wood floor coating.

Product Packaging*



PROD CODE: 702FS
SIZE: 2.50 US gallons (9.5 liters)
ORDER QTY: 2 per case



PROD CODE: 702MPE
SIZE: 1.06 US gallons (4 liters)
ORDER QTY: 4 per case

*Multi-Language Label.

* Special packaging for specific requirements available upon request.

Recommended Floor Surfaces:

All commercial wood floors.

Directions for use: INITIAL APPLICATION ON BARE WOOD FLOOR

1. Dust mop the floor using an untreated dust mop and vacuum.
2. Tack the floor with water or odorless mineral spirits using dust mop frame and turkish towels. Wring out towels and place on the floor. Place dust mop frame on top of towels and overlap towels over frame. Multiple towels are required for this job. When tacking, overlap each lane.
3. Apply two coats of WOODPRIME™ Sanding Sealer with a T-bar applicator. Allow 1-2 hours between coats.
4. Lightly sand after each coat of sealer has dried using a 175 rpm floor machine and wood floor screens (180 grit recommended) or maroon buffing pad.
5. Dust mop the floor using an untreated dust mop, and vacuum the floor.
6. Tack the floor again using turkish towels immersed in water from a clean mop bucket as in Step 2.
7. Apply 2 coats of WOODSTAR Wood Floor Coating. Let dry for 1-2 hours between coats. Floor will be fully cured in 3 days at normal temperature and humidity.

OPTIONAL: After the floor has cured completely, dust mop and burnish to a wet-look shine using an Amano Pioneer Eclipse UHS burnisher with a Blue Blend pad.

Directions for use: RECOAT OVER EXISTING WOODSTAR COATING

1. Dust mop the floor using an untreated dust mop.
2. Screen the floor using a 175 rpm floor machine and wood floor screens or maroon buffing pad.
3. Dust mop the floor again and vacuum to remove excess dust.
4. Tack the floor using turkish towels as in Step 2 under initial application.
5. Apply 1-2 coats of WOODSTAR Wood Floor Coating. Allow 1-2 hours between coats. Floor will be fully cured in 3 days at normal temperature and humidity.

OPTIONAL: After the floor has cured completely, burnish to a wet-look shine using an Amano Pioneer Eclipse UHS burnisher with a Blue Blend pad.

Product Data:

Description	Acrylic silicone hybrid polymer	Coverage	800 to 1500 ft ² /gal 20 to 37 m ² /liter	Buffability	Excellent
Appearance	Milky white liquid	Fragrance	Characteristic	Detergent Resistance ASTM D3207-92 (2008)	Excellent
Non-volatile solids ASTM D2834-95 (2008)	31%	Slip Resistance UL TM410	Meets requirements	Drying Time	1 - 2 hours per coat
Specular Gloss (60°) ASTM D1455-87 (2008)	>85	Shelf Life ASTM D1791-93 (2008)	1 year	Freeze/Thaw ASTM D3209-93 (2008)	Passes 3 Cycles
Viscosity (Brookfield) @ 68°F (20°C)	<50 centipoise	Density ASTM D1475-98 (2008)	8.7 lb/gal @ 68°F 1.05 kg/L @ 20°C	VOC (40 CFR Part 59 Subpart D)	215 g/L

MSDS sheets available for download at www.pioneer-eclipse.com



Floor Coating and Finishing materials
as to slip resistance only. 42E6

Pioneer Eclipse®

©2011 Amano Pioneer Eclipse Corporation® • 1 Eclipse Road • PO Box 909 • Sparta, NC 28675 USA
1-800-367-3550 • 1-336-372-8080 • Fax: 1-336-372-2895 • www.pioneer-eclipse.com